

上海宏骏科技有限公司 Shanghai Hongjun Science & Technology Co., Ltd.



报告编号 Report No.: HJ-QT-241391

第1页共4页

ASTM D6007-22 人造板小气候箱甲醛释放量检测

ASTM D6007-22 Standard Test Method for Determining Formaldehyde Concentrations in Air from Wood Products Using a Small-Scale Chamber CARB P2 - EPA TSCA Title VI

检测指告

委托单位	宿州市中盛木业有限公司
Applicant _	Suzhou Zhongsheng Wood Industry Co., Ltd.
工厂编号 Mill No.	ICTT-17031
样品类型 Sample Type _	单板芯的硬木胶合板 HWPW-VC
检测类别 Test Purpose _	常规检测 Quality Control Test
签 发 日 期 Report Date	2024-06-07

Shanghai Hongjun Science & Technology Co., Ltd is California Air Resources Board (CARB) & EPA approved as a



上海宏骏科技有限公司 Shanghai Hongjun Science & Technology Co., Ltd.



报告编号 Report No.: HJ-QT-241391

第2页共4页

注 意 事 项 Intentions

- 1. 报告无检测单位"检测专用章"无效; The testing report is invalid when there is no Chinese words stamp which means "Specfic Stamp for Testing Report".
- 2. 复印报告未重新加盖检测单位"检测专用章"无效,未经本公司书面授权,不得部分复制本报告; The copy of this testing report is invalid when is is no fresh Chinese words stamp. The testing report is not permitted to be full or partly copied without the written authorization of the inspection institution.
- 3. 若需以电话、传真或其它方式传送检测结果时,所发内容只作参考,以正式书面报告为准; If the testing result needs to be presented by telephone, fax or in any other way, the presenting message is only for reference. The results of the test are subject to the formal written report.
- 4. 报告涂改无效,无编制、审核、批准人签章无效;
 This testing report that is altered would be invalid and this testing report without the signatures of the one who prepares the report, the auditor and approver shall be invalid.
- 5. 本检测报告仅对来样负责; This testing report is responsible for the received samples only.
- 6. 对检测报告若有异议,应于收到报告之日起_5_日内向检测单位提出,逾期不予受理; If there is any objection to the testing report, it should be presented to the testing institution within 5 days from the date of receiving the test report. The objection shall not be accepted after the expiry of the prescribed time limit.

公司注册地址 Registration address: 上海市闵行区光华路 598 号 3 幢 1 楼 103-9


检测地址 Test address: 重庆市江北区港安二路 8 号 3 号楼 6F

邮政编码 Post code: 400025 电 话 Tel: 023-63525678

传 真 Fax: <u>023-63530958</u> E-mail: <u>lab@icttglobal.org</u>



上海宏骏科技有限公司





报告编号 Report No.: HJ-QT-241391

第3页共4页

		样品信息 Samp	le Information						
生产单位	宿州市中盛木业有阳		10 11101 111111011						
MFG Name	1自州中 中 金 本 业 有 限 公 可 Suzhou Zhongsheng Wood Industry Co., Ltd.								
委托单位	Suznou Znongsneng wood Industry Co., Ltd. 宿州市中盛木业有限公司								
Applicant	Suzhou Zhongsheng Wood Industry Co., Ltd.								
Пррпеши									
样品类型	HWPW-VC			Wood Species	杨木 Poplar				
Sample Type	表面处理 Surface Coated: 是 Yes□ 否 No☑ 单面 Single□ 双面 Double-side□								
样品规格及数量				DV II IF PX					
Sample	150*	250mm 1Set (3 PCS	S/Set)	样品厚度	15mm-7Plies				
Quantity& Size				Sample Thickness					
生产日期	2024.05.22	采样日期	2024.05.24	收样日期	2024-05-28				
Production Date	2024-05-23	Sample Date	2024-05-24	Sample Received					
产品/批次号	20240522	样品描述		1					
Product/Batch ID	20240523	Sample Description							
羊品包装状态 Sample ————————————————————————————————————		密封完好 Packaging we g箱法)Formaldehyde		ale Chamber)					
Test Item									
检测依据	ASTM D6007-22: Standard Test Method for Determining Formaldehyde Concentrations in Air from Woo								
Test Standard		11 0 1 01 1	•		is in the from wo				
烟户 6:10	Froducts Using a Sm	all-Scale Chamber			is in 7th Hom wo				
判定依据				及加州空气资源局 931:					
Conformity Standard									
Conformity Standard 检测日期	美国联邦法案 40 CF		A Title VI)第§770.10	报告日期					
Conformity Standard	美国联邦法案 40 CF 20 送检的样品经检测 7	FR Part 770(EPA TSCA) 024-05-29 至 2024-06-0	A Title VI)第§770.10 05 ested:		20 法规				
Conformity Standard 检测日期	美国联邦法案 40 CF 20 送检的样品经检测 7 甲醛释放量 (FR Part 770(EPA TSCA 024-05-29 至 2024-06-0 The samples had been to (小气候箱法)参照 A	A Title VI)第§770.10 05 ested: STM D6007-22 标准	报告日期 Report Date	20 法规 2024-06-07				
Conformity Standard 检测日期 Test Date	美国联邦法案 40 CF 20 送检的样品经检测了 甲醛释放量(Formaldehyde	FR Part 770(EPA TSCA 024-05-29 至 2024-06-0 The samples had been to (小气候箱法)参照 A	A Title VI)第§770.10 05 ested: STM D6007-22 标准	报告日期 Report Date 进行检测,检测结果参	20 法规 2024-06-07				
Conformity Standard 检测日期 Test Date 检测结论	美国联邦法案 40 CF 20 送检的样品经检测了 甲醛释放量(Formaldehyde	FR Part 770(EPA TSCA 024-05-29 至 2024-06-(The samples had been to (小气候箱法) 参照 A e emission per ASTM D	A Title VI)第§770.10 05 ested: STM D6007-22 标准	报告日期 Report Date 进行检测,检测结果参 lber), see test result on pa	20 法规 2024-06-07				
Conformity Standard 检测日期 Test Date 检测结论	美国联邦法案 40 CF 20 送检的样品经检测了 甲醛释放量(Formaldehyde	FR Part 770(EPA TSCA 024-05-29 至 2024-06-0 The samples had been to (小气候箱法) 参照 A e emission per ASTM D	A Title VI)第§770.10 05 ested: STM D6007-22 标准 06007-22 (small cham	报告日期 Report Date 进行检测,检测结果参lber), see test result on pa	20 法规 2024-06-07				
Manage Conformity Standard 检测日期 Test Date 检测结论 Conclusion	美国联邦法案 40 CF 20 送检的样品经检测了甲醛释放量(Formaldehyde)详见检测信息	FR Part 770(EPA TSCA 024-05-29 至 2024-06-0 The samples had been to (小气候箱法) 参照 A e emission per ASTM D ! See test data.	A Title VI)第§770.10 05 ested: STM D6007-22 标准 06007-22 (small cham 检测单位(检 Testing unit (special	报告日期 Report Date 进行检测,检测结果参lber), see test result on pa	20 法规 2024-06-07				
Marie Conformity Standard 检测日期 Test Date 检测结论 Conclusion 备注	美国联邦法案 40 CF 20 送检的样品经检测了 甲醛释放量(Formaldehyde 详见检测信息 1.样品信息由委托单 Applicant to provide	FR Part 770(EPA TSCA 024-05-29 至 2024-06-0 The samples had been to (小气候箱法) 参照 A the emission per ASTM D the See test data .	A Title VI)第§770.10 05 ested: STM D6007-22 标准 06007-22 (small cham 检测单位(检 Testing unit (special	报告日期 Report Date 进行检测,检测结果参lber), see test result on pa	20 法规 2024-06-07				
Manage	美国联邦法案 40 CF 20 送检的样品经检测了 甲醛释放量(Formaldehyde 详见检测信息 1.样品信息由委托单 Applicant to provide 2.根据标准要求,样	FR Part 770(EPA TSCA 024-05-29 至 2024-06-0 The samples had been to (小气候箱法) 参照 A the emission per ASTM D the See test data .	A Title VI)第§770.10 05 ested: STM D6007-22 标准 06007-22 (small cham 检测单位(检 Testing unit (special	报告日期 Report Date 进行检测,检测结果参iber), see test result on pa 测专用章) seal for testing)	20 法规 2024-06-07				



上海宏骏科技有限公司





Shanghai Hongjun Science & Technology Co., Ltd.

报告编号 Report No.: HJ-QT-241391

第4页共4页

检测信息 Test Data

样品在检测前封边放置在温度为 24℃±3℃(75°F±5°F)和相对湿度为 50±5%的条件下调节,样品调节的甲醛背景浓度低于 0.10ppm.

The samples were covered the edges with aluminum tape, stored at conditions of $50\pm5\%$ RH, $24^{\circ}C\pm3^{\circ}C(75^{\circ}F\pm5^{\circ}F)$. The formaldehyde background concentration in the air where the specimens were conditioned was documented at <0.10 ppm.

然后将样品放入甲醛背景浓度低于 0.02ppm 的气候箱(体积为 0.2 m³)中,气候箱维持温度 25 ℃±1 ℃(77°F±2°F) ,湿度 50±4%,进气的甲醛浓度低于 0.02ppm,至少 3 次完全空气置换后,以 1L/min±0.05L/min 的速度采箱体内空气 30 分钟,以分光光度计 7230G 进行分析。甲醛释放量值修正到相对湿度 50%,温度 77 °F 的标准值。

Then put the sample into the chamber (volume = 0.2 m^3), and which was maintained at $25^{\circ}\text{C} \pm 1^{\circ}\text{C}$ (77°F±2°F) and 50±4%. The formaldehyde concentration of make-up air and the chamber were both measured at <0.02 ppm. After allow time for no less than three full air changes, air samples were drawn at a rate of $1L/\text{min} \pm 0.05L/\text{min}$ for 30 minutes. Emission values were determined with spectrophotometer analysis 7230G.

The Formaldehyde Emissions are corrected to an emission level at standard conditions (50% RH and 77 °F).

样品	背靠背检测	箱 Q/A 值	厚度	暴露面积	平均进	时间	温度	相对	甲醛释放量
编号	日非月位例 Tested	Chamber	Thickness	Total Exposed	气流量	Time	Temp.	湿度	Formaldehyde
Sample		Q/A Ratio	Tillekiless	Area	Flow	Tillic	Temp.	RH	Emission
No.	back-to-back	$(m^3/h)/m^2$	(mm)	(m^2)	(L/min)	(h)	(℃)	(%)	(ppm)
241391	No	1.175	15	0.225	4.41	2.83	24.6	53.0	0.042

ASTM D6007-22 检测结果满足美国联邦法案 40 CFR Part 770(EPA TSCA Title VI)第§770.10 及加州空气资源局 93120 法规表格一中要求的单板芯的硬木胶合板第二阶段 0.05ppm 的限值要求。

The ASTM D6007-22 test result meets the §770.10 of 40 CFR Part 770 (EPA TSCA Title VI) & CARB 93120, Table 1, Phase 2 limitation of 0.05ppm for HWPW-VC.

附注 Note:

- 1. ASTM D6007-22 甲醛释放量检测在本实验室方法检出限(MDL)为 0.004ppm,低于 0.004ppm 视为未检出。The method detection limit in our laboratory for this method is 0.004ppm, Thus if the test result is less than 0.004ppm,it is regarded as not detect out HCHO.
- 2. 客户申请的测试判定规则为: IEC Guide 115:2007 第二程序—准确度法,不需要考虑不确定度。The applicable decision rules of this test are: IEC Guide 115:2007 Procedure 2 Accuracy method,do not subject to measurement uncertainty.